



НҮҮРСНИЙ ОВООЛГЫН ҮЗҮҮЛЭЛТ

№DPP



НҮҮРСНИЙ ОВООЛГЫН ЧАНАРЫН ДУНДАЖ ҮЗҮҮЛЭЛТ

НИЙТ ЧИЙГ

TM (ar)

 $\leq 9.0\%$

Нийт хүхэр S (db)

1.5%

(-0.3; +0.5)

ДЭГДЭМХИЙ БОДИС

VM(daf)

 $>20-37\%$

ИЛЧЛЭГ (ar)

 >4000

БАРЬЦАЛДАХ

ЧАНАР

 $>5-30$

ALS GROUP LLC

Mongol Nekhmel Building, 19nd khoroo
Chinggis Avenue, Khan-Uul District
Ulaanbaatar, Mongolia
Tel +976 70 007667



CERTIFICATE OF ANALYSIS
26J08-TT

CLIENT: Tavantolgoi LLC

ADDRESS: Umnugovi, Tsogttsetsii
Tsagaan ovoo bag
Tavantolgoi LLC

ATTN: Altan-Ulzii.E

PROJECT NO. xxx

LAB. JOB NO. 26J08-TT

NO. SAMPLES:

Notes/Comments: xxx

SAMPLES RECEIVED: 08/Oct/26
INSTRUCTIONS RECEIVED: 08/Oct/26
DATE OF REPORT: 09/Oct/26
STATUS OF REPORT: FINAL
ANALYSIS COMPLETE: 09/Oct/26
PREPARATION CODE: CRUSH-01, 02; MILL-01
ANALYSIS CODE: TM, MOIS, ASH, VOL, TSUL,
GCV, CSN, CKIN

APPROVED BY: Laboratory Manager
B.Bold-Erdene



These test results are representative only of the sample received in the laboratory.

STANDARD METHOD		GB/T 211	GB/T 212	GB/T 212	GB/T 212	ISO 19579	GB/T 213	GB/T 212	GB/T 212	GB/T 212	GB/T 212	ISO 19579	GB/T 213
LAB NO.	SAMPLE NO.	AS RECEIVED BASIS						AIR DRIED BASIS					
		Total Moisture (TM)	Ash (ASH)	Volatile Matter (VOL)	Fixed Carbon (FC)	Total Sulphur (TSUL)	Gross Calorific Value (GCV)	Moisture (MOIS)	Ash (ASH)	Volatile Matter (VOL)	Fixed Carbon (FC)	Total Sulphur (TSUL)	Gross Calorific Value (GCV)
				%			kcal/kg			%			kcal/kg
1	DPP_261008_1	2.61	36.84	20.52	40.03	1.38	4833	1.04	37.44	20.85	40.68	1.40	4911
2	DPP_261008_2	2.55	35.35	20.42	41.67	1.71	4920	1.01	35.91	20.74	42.33	1.73	4997

QUALITY ASSURANCE/QUALITY CONTROL DATA

STDALSWS-41/25	ASH	VOL	GCV	TSUL
Certified Value	10.93	20.61	7691	0.680
Standard Deviation	0.049	0.076	12	0.007
Unit	%	%	kcal/kg	%
Analyzed value	10.94	20.59	7689	0.684

ALS GROUP LLC

Mongol Nekhmel Building, 2nd khoroo
Chinggis Avenue, Khan-Uul District
Ulaanbaatar, Mongolia
Tel +976 70 007667

**CERTIFICATE OF ANALYSIS
26J08-TT**

CLIENT: Tavantolgoi LLC
ADDRESS: Umnugovi, Tsogttsetsii
Tsagaan ovoo bag
Tavantolgoi LLC
ATTN: Altan-Ulzii.E
PROJECT NO. xxx
LAB. JOB NO. 26J08-TT
NO. SAMPLES:
Notes/Comments: xxx

SAMPLES RECEIVED: 08/Oct/26
INSTRUCTIONS RECEIVED: 08/Oct/26
DATE OF REPORT: 09/Oct/26
STATUS OF REPORT: FINAL
ANALYSIS COMPLETE: 09/Oct/26
PREPARATION CODE: CRUSH-01, 02; MILL-01
ANALYSIS CODE: TM, MOIS, ASH, VOL, TSUL,
GCV, CSN, CKIN

These test results are representative only of the sample received in the laboratory.

STANDARD METHOD		GB/T 212	GB/T 212	GB/T 212	ISO 19579	GB/T 213	GB/T 212	GB/T 212	ISO 19579	GB/T 213	GB/T 5448	GB/T 5447		
LAB NO.	SAMPLE NO.	DRY BASIS					DRY, ASH-FREE BASIS					Crucible Swelling Number (CSN)	Coal Caking Index (CKIN)	
		Ash (ASH)	Volatile Matter (VOL)	Fixed Carbon (FC)	Total Sulphur (TSUL)	Gross Calorific Value (GCV)	Volatile Matter (VOL)	Fixed Carbon (FC)	Total Sulphur (TSUL)	Gross Calorific Value (GCV)				
		%				kcal/kg	%				kcal/kg			
		5:1	3:3											
1	DPP_261008_1	37.83	21.07	41.11	1.41	4963	33.88	66.12	2.27	7982	1.0	-	16	
2	DPP_261008_2	36.28	20.96	42.77	1.75	5049	32.89	67.11	2.75	7923	1.0	-	16	